

S-3301 (GIP S-6303)

Sheet Stock

Conductive Elastomer Gasket

Characteristics:

The shielding effectiveness of TennVac's S-3301 is designed to replace high cost Ag plated particles at a fraction of the cost. The nature of the Ni plated Graphite particles not only provides reasonable Electrical conductivity but also Absorption property.

It is a two component, heat curable Silicone system, optimized for our proprietary sheet stock process.

The system offers enhanced galvanic corrosion resistance and stability in severe environments.

Applications:

- Base Station
- Telecommunication Devices

Typical Properties:

Properties	Unite	S-3301
Elastomer Binder		Silicone
Conductive Filler		Ni/Gr
Physical Properties		
Specific Gravity	g/cm	2.0
Shore A Hardness		60
	psi	150
	%	80
	lb/in	40
Compression Set	%	30
Color		Dark Grey
Temperature Range	°C	-45 ~+150
	°C	200
Electrical Properties		
Volume Resistivity	Ohm .cm	0.08
E-Field, 100 MHz	dB	
	dB	
	dB	

This information and our technical advise – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advise does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are

TennVac Inc. www.tennvac.com

Tel: +886 2 2695-1213 Fax: +886 2 2695-1187 Email: Sales@tennvac.com

Address: 4F, No. 31-1, Lane 169, Kang-Ning St., Hsi-Chi City, Taipei Hsien, Taiwan

2006 version



beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

EMI / Thermal / RF Specialist

TennVac Inc. www.tennvac.com

Tel: +886 2 2695-1213 Fax: +886 2 2695-1187 Email: Sales@tennvac.com
Address: 4F, No. 31-1, Lane 169, Kang-Ning St., Hsi-Chi City, Taipei Hsien, Taiwan

2006 version